



CRESTAKYD[®] 30-5028

Short oil alkyd

INTRODUCTION CRESTAKYD 30-5028 exhibits rapid drying characteristics and fast hardness development. It has very good weather resistance, excellent film build and attractive gloss.

CHARACTERISTICS (Not to be taken as a specification)

Appearance		Clear, bit free
Solids content	%	60 ± 1.5
Oil type		Castor Oil
Oil content	%	45
Solvent		Xylene
Acid value (base resin)	mg KOH/g	max. 20
OH-number (base resin)	mg KOH/g	~115 (3,5 %)
Efflux time, 50% NVC in Xylene, DIN cup 4, @ 20°C		140-220 s
Gardner Colour	max. 8	

APPLICATIONS

CRESTAKYD 30-5028 can be used for NC finishes, acid hardening finishes and in combination with low reactivity melamine resins for industrial stoving enamels and automotive finishes.

PACKAGING

CRESTAKYD 30-5028 can be supplied in drums, road-tankers and in containers.

STORAGE

CRESTAKYD 30-5028 can be stored in the containers in which it was supplied.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

Issue No.1

Scott Bader Company Limited
Wollaston, Wellingborough, Northamptonshire, NN29 7RL
Telephone: +44 (0) 1933 663100 Facsimile: +44 (0) 1933 666529

