

TEXICOTE[®] 03-084

Vinyl acetate homopolymer emulsion

INTRODUCTION

TEXICOTE 03-084 is high viscosity vinyl acetate homopolymer emulsion, stabilised with polyvinyl alcohol. It can be used as an adhesive and as adhesive bases in a wide range of applications.

CHARACTERISTICS (Not to be taken as a specification)

Solids content	%	51
Viscosity at 25°C (Rheomat, Mobil 3, 25 s-1)	dPa.s	42
pH		5
Minimum film formation temperature *	°C	15
Glass Transition temperature	°C	37

* Determined by metal bar with temperature gradient.

APPLICATIONS

TEXICOTE 03-084 is recommended as a base emulsion for wet bond adhesives because of its high viscosity and wet-tack. TEXICOTE 03-084 is also recommended as a base for wood and general purpose adhesives in the building industry and as a cement additive to promote adhesion to sub-floors and improve anti-dusting properties.

PACKAGING

TEXICOTE 03-084 may be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

STORAGE

TEXICOTE 03-084 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate material safety data sheet

Issue No. 4 Nov-16

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com