

TEXICRYL[®] 13-309

Carboxylated acrylic copolymer emulsion

INTRODUCTION

Texicryl 13-309 is a carboxylated acrylic copolymer emulsion designed for use as a thickener in emulsion paints and for thickening various adhesive compounds.

CHARACTERISTICS (Not to be taken as a specification)

| | | |
|---|-------|-----|
| Solids content | % | 35 |
| Viscosity at 25°C, (Brookfield RVT, Spindle 2, 100 rpm) | mPa s | 50 |
| pH | | 3.0 |
| Minimum film formation temperature* | °C | 10 |
| Glass transition temperature | °C | 42 |

* Determined by metal bar with temperature gradient.

APPLICATIONS

Thickener for use in artist's paints, adhesives and textile coatings. Texicryl 13-309 helps balance rheological properties of a paint and aids application / flow properties.

PACKAGING

Texicryl 13-309 is supplied in drums and 1 tonne IBC's. Bulk deliveries are supplied by road tanker.

STORAGE

Texicryl 13-309 can be stored in containers supplied and protected from frost and extended exposure to direct sunlight.

HEALTH & SAFETY

Please see separate material safety data sheet

Issue No. 5 Nov-16

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com