

TEXICRYL[®] 13-526

Styrene acrylic copolymer emulsion

INTRODUCTION

Texicryl 13-526 is a high performance styrene acrylic copolymer emulsion designed for use in cold seal adhesive applications.

CHARACTERISTICS (Not to be taken as a specification)

Solids content	%	50
Viscosity at 25°C, (Brookfield RVT, Spindle 2, 20 rpm)	mPa s	200
pH		4.5
Minimum film formation temperature*	°C	12
Glass transition temperature	°C	19

* Determined by metal bar with temperature gradient.

APPLICATIONS

Cold seal adhesives.

PACKAGING

Texicryl 13-526 is supplied in 1 tonne IBC's. Bulk deliveries are by road tanker.

STORAGE

Texicryl 13-526 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH & SAFETY

Please see separate material safety data sheet

Issue No. 3 Nov-16

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com