



TEXICRYL[®] AD9122

Modified Styrene Acrylic copolymer

INTRODUCTION

TEXICRYL AD9122 is a modified styrene acrylic copolymer emulsion that offers excellent water resistance and adhesion to various substrates including wood, rubber and metal.

CHARACTERISTICS (Not to be taken as a specification)

Solids content	%	45 – 47
Viscosity at 25°C (Brookfield RV, Spindle 4, 20 rpm)	cps	150 – 4500
pH	-	8.5 – 9.2
Particle size	nm	70 - 175
Relative density at 25°C		1.05
Emulsifying System		Anionic
Tg	°C / °F	12 / 54

APPLICATIONS

TEXICRYL AD9122 has been designed for the formulation of low VOC waterbased coatings. Because of its excellent adhesion to various substrates and water resistance, it can be formulated as mulch coatings for various mulch substrates.

TEXICRYL AD9122 is Alkyl Phenol Ethoxylate free.

PACKAGING

TEXICRYL AD9122 is supplied in a 460 lb. net weight plastic drum.

STORAGE

TEXICRYL AD9122 can be stored in the containers in which it is supplied.

Protect from temperatures below 40°F.

HEALTH & SAFETY

Please see separate Material Safety Data Sheet.

9/10

NOTICE

The information and recommendations in this publication are, to the best of our actual knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Scott Bader and users of these products should make their own tests to determine the suitability of these products for their own particular purposes. Because of numerous factors beyond our control affecting the results of the use of these products, SCOTT BADER, INC. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, OTHER THAN THAT THE PRODUCTS CONFORM TO ITS APPLICABLE CURRENT STANDARD SPECIFICATION.

Suggestions for uses of our products should not be understood as recommending the use of our products in violation of any patent.