

CRYSTIC[®] 123PA and CRYSTIC[®] 124PA

General Purpose Polyester Resins

Introduction

Crystic 123 PA is a medium thixotropic tropicalised pre-accelerated, waxed unsaturated polyester resin.

Crystic 124 PA is a non-thixotropic tropicalised pre-accelerated, waxed unsaturated polyester resin. These resins can also be supplied un-waxed.

These resins have been specially formulated to give rapid wetting and impregnation of the reinforcement and are ideally suited for the building of boats, water tanks, bath tubs, shower trays and other products where water resistance is an important factor.

Formulation

The following formulations are recommended for laminating.

Parts by Weight	Formulation
Crystic 123PA	100
Crystic 124PA	
Catalyst M or MEKP M-50	1 – 2.5

Curing should not be carried out at temperature below 150C and the resin must be allowed to attain workshop temperature before being formulated for use.

These resins require the addition of catalyst only to start the curing reaction. The catalyst must be thoroughly stirred in the resin.

Gel Time

The amount of catalyst and the ambient temperature control the gel time of the resin formulation. The following table shows the gel time of 100 pbw Crystic 123 or 124 containing various levels of Catalyst M.

Parts of Catalyst to 100 parts of catalysed resins	1.0	1.5	2.0
Gel time in minutes at 25°C	37.5	23.25	16.5
Gel time in minutes at 30°C	29	18	12.5

Typical Properties

Typical properties of the liquid resins.

Property		Crystic 123PA	Crystic 124PA
Appearance		Cloudy	Clear
Viscosity at 25°C CPS (Brookfield LVF viscometer spindle 3 at 60 RPM)		500	400
Specific Gravity at 25°C		1.12	1.11
Acid value	mg KOH/g	24	24
Volatile Content	%	37	38

Typical properties of fully cured resins (unfilled casting) using test methods as in BS 2782 : 1980.

Property		Typical Value
Barcol Hardness (Model GYZJ 934 -1)		45
Water Absorption 24 h at 23°C	mg	18
Deflection Temperature under Load (1.80 MPa)	°C	69
Specific Gravity at 25°C		1.21
Elongation at Break at 20°C	%	2.1
Tensile Strength	MPa	65
Tensile Modulus	MPa	3800

Typical properties of a Crystic 123PA *CSM Laminate using test methods as in BS 2782 : 1980.

Property		Cure 1	Cure 2
Glass Content	%	32	32
Tensile Strength	MPa	122	117
Tensile Modulus	MPa	8500	8400
Elongation at Break	%	2.0	2.0
Flexural Strength	MPa	183	174
Flexural Modulus	MPa	6300	5700

* Made with 4 layers of 450g/m² mat
Cure 1 – 24 hours at 20°C, 16 hours at 40°C
Cure 2 – As Cure 1, then after 2 hours boil in water (tested wet)

Storage

Crystic 123PA and Crystic 124PA should be stored in the dark in suitable closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use.

Packaging

Crystic 123PA and Crystic 124PA are supplied in 225kg steel containers. For shipping purposes they are Class 3.3 in the IMCO Code (page 3379).

Health & Safety

Please see separate Material Safety Data Sheet.

Version 2 : February 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com