

CRYSTIC[®] FIREGUARD 73PA

Fire Retardant Brush Gelcoat

Introduction

Crystic Fireguard 73PA is a pre-accelerated filled brush gelcoat. It is available in a wide range of colours and the information contained in this technical data sheet also applies to these pigmented versions.

Applications

Crystic Fireguard 73PA can be used both internally and externally for building, transport and general industrial work.

Features and Benefits

Crystic Fireguard 73PA has very low flammability.

Formulation

Crystic Fireguard 73PA should be allowed to attain workshop temperature (18°C-20°C) before use. Stir well by hand or with a low shear stirrer to avoid aeration and then allow to stand to regain thixotropy. Crystic Fireguard 73PA requires only the addition of catalyst to start the curing reaction. The recommended catalyst is Butanox M50 (or other equivalent catalyst) which should be added at 2% into the gelcoat. (Please consult our Technical Service Department if other catalysts are to be used). The catalyst should be thoroughly incorporated into the gelcoat, with a low shear mechanical stirrer where possible.

Application

For normal moulding, the application of Crystic Fireguard 73PA should be controlled to 0.4 - 0.5mm (0.015 - 0.020 inch) wet film thickness. As a guide, approximately 550-750g/m² of gelcoat mixture (depending on pigment) will give the required thickness when evenly applied.

Additives

The addition of fillers or pigments to Crystic Fireguard 73PA is likely to affect the weathering and cure of this material and is not recommended.

Recommended Testing

It is recommended that customers test Crystic Fireguard 73PA before use under their own conditions of application to ensure the required surface finish is achieved.

Physical Data - Uncured

The following tables give typical properties of Crystic Fireguard 73PA when tested in accordance with SB, BS EN or BS EN ISO test methods.

| Property | Unit | Liquid Gelcoat |
|--|---------|------------------|
| Appearance | | Opaque, Coloured |
| Viscosity at 25 °C | | Thixotropic |
| Specific Gravity at 25 °C | | 1.40 |
| Stability at 20°C | Months | 3 |
| Gel time at 25°C using 2% Butanox M50 (or Other Equivalent Catalyst) | Minutes | 6 - 10 |

Physical Data - Uncured

| Property | Unit | Fully Cured* Gelcoat (Unfilled Casting) |
|---|------|--|
| Barcol Hardness (Model GYZJ 934-1) | | 52 |
| Deflection Temperature Under Load† (1.80 MPa) | °C | 78 |
| Elongation at Break | % | 1.7 |
| Tensile Strength | MPa | 57 |
| Tensile Modulus | MPa | 5400 |

*Curing Schedule - 24 hrs at 20°C, 3 hrs at 80°C.

† Curing Schedule - 24 hrs at 20°C, 5 hrs at 80°C, 3 hrs at 120°C.

Post-Curing

For many applications, Crystic Fireguard 73PA will perform adequately when cured at workshop temperature (20°C). However, for optimum properties it should be allowed to cure for 24 hours at 20°C, and then be oven-cured for 3 hours at 80°C.

Storage

Crystic Fireguard 73PA should be stored in its original container and out of direct sunlight. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use.

Packaging

Crystic Fireguard 73PA is supplied in 25Kg and 225Kg containers.

Health and Safety

Please see separate Material Safety Data Sheet.

Version 3 : October 2015

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com