

CRYSTIC[®] 2-406PA

Introduction

Crystic 2-406PA is a pre-accelerated, thixotropic polyester resin, with low styrene emission. Its rapid impregnation of glass fibre reinforcements, and low exotherm temperature, make it ideal for multi-layer laminates, in spray or hand lay applications.

Crystic 2-406PA is recommended for the manufacture of boat hulls, vehicle bodies and industrial mouldings.

During the laminating phase, styrene emissions from Crystic 2-406PA are considerably reduced compared with a normal resin. Levels significantly lower than current or proposed legislation can be attained. This reduction in styrene emission is achieved with no loss of interlaminar adhesion.

A colour change mechanism is included in the formulation. When catalyst is added the resin will change colour from a pale blue to green, this will then clear as the resin cures.

Approvals

Crystic 2-406PA is approved by Lloyd's Register of Shipping for the construction of craft under their survey.

It also meets the requirements of BS 3532 : 1990 : Type A

Formulation

Crystic 2-406PA should be allowed to attain workshop temperature (18°C - 20°C) before use. It needs only the addition of a catalyst to start the curing reaction. The recommended catalyst is Catalyst M (or Butanox M50). The catalyst should be added at 1% or 2% into the resin and thoroughly dispersed, shortly before use.

The geltime of the resin can be approximately determined from the table below.

Pot Life

Parts of Catalyst M to 100 Parts Crystic 2-406 PA	1.0	2.0
Pot life in Minutes at 15°C	36	23
Pot life in Minutes at 20°C	22	16
Pot life in Minutes at 25°C	16	11

The resin, mould and workshop should be at, or above, 15°C before curing is carried out.

Additives

The addition of certain pigments, fillers or extra styrene may adversely affect the properties of Crystic 2-406PA. Users should seek advice from our Technical Service Department before making any additions.

Post Curing

Satisfactory laminates for many applications can be made from Crystic 2-406PA by curing at workshop temperature (20°C). For optimum properties and long term performance, however, laminates should be post cured before being put into service. The laminate should be allowed to cure for 24 hours at 20°C, and then be oven cured for 3 hours at 80°C or 16 hours at 40°C.

Typical Properties

The following tables give typical properties of Crystic 2-406PA when tested in accordance with BS 2782.

Property		Liquid Resin
Appearance		Pale Blue
Viscosity at 25°C 37.35 sec ⁻¹	poise	4.4
Viscosity at 25°C 4500 sec ⁻¹	poise	2.5
Specific Gravity at 25°C		1.10
Volatile Content	%	41
Acid Value	mg KOH/g	16
Stability at 20°C	months	3
Geltime at 25°C using 1% Catalyst M (or Butanox M50)	Minutes	16
Property		Fully Cured* Resin (unfilled casting)
Barcol Hardness (Model GYZJ 934-1)		45
Deflection Temperature under load † (1.80 MPa)	°C	62
Water Absorption 24 hours at 23°C	mg	14
Tensile Strength	MPa	54
Tensile Modulus	MPa	3700
Elongation at Break	%	1.7
Specific Gravity at 25°C		1.20
Volumetric Shrinkage	%	8.35

* Curing Schedule - 24 hrs at 20°C, 3 hrs at 80°C

† Curing Schedule - 24 hrs at 20°C, 5 hrs at 80°C, 3 hrs at 120°C

Property		C.S.M** Laminate	
		P.B	E.B
Glass Content	%	29.3	27.4
Tensile Strength	MPa	113	74
Tensile Modulus	MPa	7500	6900
Elongation at Break	%	1.8	1.3
Flexural Strength	MPa	224	196
Flexural Modulus	MPa	6900	6800

** Made with 4 layers 450g/m CSM
Curing schedule - 24hrs at 20°C, 16hrs at 40°C

Typical interfacial properties of a Crystic 2-406PA chopped strand mat laminate

Property	Test Method	Normal *	Resin-rich**
Unnotched Charpy impact strength kJ/m ²	ISO 179	72	70
Single lap shear strength MPa	BS 4994 Appendix C	3.8	3.9
Short beam shear strength MPa	BS 2782 Method 341A	22 (18.6†)	21 (19.4†)
Fracture surface energy J/m ²	Scott Bader test	350	300

*24hrs delay between 2 lay-ups of 2 x 450 g/m² chopped strand mat
**2 x 450 g/m² CSM. Allowed to gel. Then 700 g/m² pure resin interface
Then 24hrs delay. Then 2 x 450 g/m² CSM.
†Data obtained using 5 days delay instead of 24hrs

Storage

Crystic 2-406PA should be stored in the dark in suitable closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use. Where they have to be stored outside, it is recommended that they are kept in a horizontal position to avoid the possible ingress of water.

Packaging

Crystic 2-406PA is supplied in 25kg and 200 kg containers. Bulk supplies can be delivered by road tanker.

Health and Safety

Please see separate Material Safety Data Sheet.

Technical Leaflet No. 174.3

Version 2 : February 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com