



CRESTAKYD®10-3000

INTRODUCTION CRESTAKYD 10-3000 is an air drying alkyd that has excellent brushability & flow

characteristics, as well as good gloss retention & weathering resistance

CHARACTERISTICS

Solid content $70 \pm 1,5\%$ Oil Type Linoleic Oil content 62%

Solvent non-aromatic WS150/200, D40

Acid values (base resin) max. 10 mgKOH/g Viscosity @ 25°C, sp3/10rpm 2500 . 5000 mPas

Colour, Gardner max. 7

APPLICATION

CRESTAKYD 10-3000 is used for interior and exterior decorative enamels, marine and topside paints. Also suitable for undercoats, maintenance primers and floor varnishes.

Decorative enamels are normally dry to touch in $2-2\frac{1}{2}$ hours and tack free after $4-4\frac{1}{2}$ hours. Through dry properties are excellent. High levels of gloss and build, coupled with good colour retention and durability properties, make the resin ideally suited for exterior work.

Drier Recommendation:

0.2% zirconium, 0.05% cobalt and 0.1% calcium, calculated as metals on resin solids or suitable %ombination driers."

Thinner recommendation: excellent tolerance to aliphatic hydrocarbon solvents.

PACKAGING CRESTAKYD 10-3000 can be supplied in drums, road-tankers and in containers.

STORAGE The resin should be stored in the original, unopened and undamaged containers

in a dry place at temperatures between 0°C and 30°C. Exposure to direct

sunlight should be avoided

HEALTH & SAFETY Please see separate Material Safety Data Sheet

Issue No. 1/14.11.2016



CROATIA, 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr





