



CRESTAKYD[®] 20-5029

Medium oil air drying alkyd

Previous Name: CHROMOSAL SU-49 60X

INTRODUCTION CRESTAKYD 20-5029 is a rapid drying alkyd that has excellent gloss / weathering resistance and flow characteristics.

CHARACTERISTICS

Solids content	60 ± 1,5%
Oil type	SBO
Oil content	49%
Solvent	Xylene,
Acid value (base resin)	max. 10 mg KOH/g
Viscosity, 60% NVC in Xylene, Brookfield, @ 25°C	400 - 1600 mPas
Gardner Colour	max. 6

APPLICATION CRESTAKYD 20-5029 can be used for primers and other air-dry industrial finishes.

PACKAGING CRESTAKYD 20-5029 can be supplied in drums, road-tankers and in containers..

STORAGE The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

HEALTH & SAFETY Please see separate material safety data sheet.

Issue No. 1



CROATIA, 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr

