



CRESTAKYD[®] 30-5016

Short oil air drying alkyd

INTRODUCTION CRESTAKYD 30-5016 is a chain stopped alkyd for rapid air drying industrial paints and low bake enamels with excellent resistance to oils, greases and water.

CHARACTERISTICS

Solid content	50±1,5%
Oil Type	Mixed Non Yellowing
Oil content	24%
Solvent	Xylene
Acid values (base resin)	max. 22 mgKOH/g
Viscosity @ 25°C, sp 4/10rpm	6 000 . 10 000mPas
Colour, Gardner	max. 6

ADDITIONAL INFORMATION

Solids content at 200 mPa·s (25°C)	35%
Relative density @ 20°C	1,01g/cm ³

APPLICATION CRESTAKYD 30-5016 is suitable for use in vehicle and machinery finishes. Can be air-dried, force-dried or stoved. Air drying finishes are tack free in 30 minutes with good through drying properties. CRESTAKYD 30-5016 has excellent resistance to oils, greases and water.

Drier Recommendation

0.05% cobalt, 0.2% zirconium: calculated as metal on resin solids.

Thinner Recommendation

Excellent tolerance to aromatic hydrocarbons, limited tolerance to aliphatic solvents.

PACKAGING CRESTAKYD 30-5016 can be supplied in drums, road-tankers and in containers.

STORAGE The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

HEALTH & SAFETY Please see separate Material Safety Data Sheet

Issue No. 1/14.11.2016



CROATIA, 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr

