



# CRESTAKYD<sup>®</sup> 30-5016

## Short oil air drying alkyd

**INTRODUCTION** CRESTAKYD 30-5016 is a chain stopped alkyd for rapid air drying industrial paints and low bake enamels with excellent resistance to oils, greases and water.

### CHARACTERISTICS

Solid content	50±1,5%
Oil Type	Mixed Non Yellowing
Oil content	24%
Solvent	Xylene
Acid values (base resin)	max. 22 mgKOH/g
Viscosity @ 25°C, sp 4/10rpm	6 000 . 10 000mPas
Colour, Gardner	max. 6

### ADDITIONAL INFORMATION

Solids content at 200 mPa·s (25°C)	35%
Relative density @ 20°C	1,01g/cm <sup>3</sup>

**APPLICATION** CRESTAKYD 30-5016 is suitable for use in vehicle and machinery finishes. Can be air-dried, force-dried or stoved. Air drying finishes are tack free in 30 minutes with good through drying properties. CRESTAKYD 30-5016 has excellent resistance to oils, greases and water.

#### Drier Recommendation

0.05% cobalt, 0.2% zirconium: calculated as metal on resin solids.

#### Thinner Recommendation

Excellent tolerance to aromatic hydrocarbons, limited tolerance to aliphatic solvents.

**PACKAGING** CRESTAKYD 30-5016 can be supplied in drums, road-tankers and in containers.

**STORAGE** The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

**HEALTH & SAFETY** Please see separate Material Safety Data Sheet

Issue No. 1/14.11.2016



CROATIA, 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: [info@scottbader.hr](mailto:info@scottbader.hr)

