



CRESTAKYD[®] 30-5068

Short oil air drying alkyd

INTRODUCTION CRESTAKYD 30-5068 is a fast drying short oil alkyd supplied in xylene for use in air-dry and force-dry primers and topcoats.

CHARACTERISTICS

Solids content	60 ± 1,5%
Oil Type	Linoleic rich
Oil Content	40%
Solvent	Xylene
Acid Value	max. 15
Viscosity, Brookfield @ 23°C sp3 / 20rpm	2000 . 4000 mPa s
Gardner Colour	max. 6

APPLICATION CRESTAKYD 30-5068 is recommended for use in air-dry and force-dry primers and topcoats in a variety of general industrial metal coating applications.

PACKAGING CRESTAKYD 30-5068 can be supplied in drums, road-tankers and in containers..

STORAGE The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

HEALTH & SAFETY Please see separate material safety data sheet.

vIssue No. 1



CROATIA , 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr

