



CRESTAKYD[®] 30-5071

Short oil alkyd

INTRODUCTION CRESTAKYD 30-5071 exhibits rapid drying characteristics and fast hardness development. It has very good weather resistance, excellent film build and attractive gloss.

CHARACTERISTICS

Solids content	70±1,5%
Oil type	Castor Oil
Oil content	45%
Solvent	Xylene
Acid value (base resin)	max. 20 mg KOH/g
OH-number (base resin)	~95 mg KOH/g (2,8 %)
Efflux time, 50% NVC in Xylene, DIN cup 4, @ 20°C	140-220 s
Gardner Colour	max. 8

APPLICATION CRESTAKYD 30-5071 can be used for NC finishes, acid hardening finishes and in combination with low reactivity melamine resins for industrial stoving enamels and automotive finishes.

PACKAGING CRESTAKYD 30-5071 can be supplied in drums, road-tankers and in containers..

STORAGE The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

HEALTH & SAFETY Please see separate material safety data sheet.

Issue No. 2



CROATIA , 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr

