



CRESTAKYD[®] 44-5043

Rosin / phenolic modified, short oil alkyd

INTRODUCTION CRESTAKYD 44-5043 is a linoleic/wood oil alkyd modified with both rosin and phenolic. It is supplied as a 60% non-volatile solution in Xylene

CHARACTERISTICS

Solid content	60 ± 1,5%
Oil Type	Linoleic / wood
Oil content	36%
Solvent	Xylene
Acid values (base resin)	max. 25 mgKOH/g
Viscosity @ 25°C, sp3/10rpm	3 000 . 6 000 mPas
Colour, Gardner	max. 8,5

APPLICATION CRESTAKYD 44-5043 has been designed for use in fast drying industrial primer applications with excellent adhesion and resistance to corrosion.

PACKAGING CRESTAKYD 44-5043 can be supplied in drums, road-tankers and in containers.

STORAGE The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided

HEALTH & SAFETY Please see separate Material Safety Data Sheet

Issue No. 1/14.11.2016



CROATIA, 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr

