# Technical Data Sheet Long Oil Air Drying Alkyd

Crestakyd° 10-2020

# **PRODUCT OVERVIEW**

CRESTAKYD® 10-2020 is a fast drying alkyd that has excellent brushability & flow characteristics, as well as good gloss retention and weathering resistance.

Alkyd Resins

| CHARACTERISTICS                                  |  |
|--|--|
| Solids Content                                   | 60±1,5%                                  |
| Oil Type   | Linoleic rich                            |
| Oil Content                                      | 67%                                      |
| Solvent  | Non-aromatic white spirit 180/220<br>D60 |
| Acid Values (base resin)                         | max. 10 mg KOH/g                         |
| Viscosity<br>(60%NVS in D60, Brookfield, @ 23°C) | 2500 - 4000 mPa s                        |
| Gardner Colour                                   | max. 6                                   |

### **APPLICATIONS**

CRESTAKYD® 10-2020 can be used for economical decorative and do-it-yourself paints, including primers, topcoats and varnishes.

### PACKAGING AND STORAGE:

CRESTAKYD® 10-2020 is available in drums, road tankers and containers.

CRESTAKYD® 10-2020 should be stored between 0 and 30°C in the original, unopened container in a dry, well ventilated place. Exposure to direct sunlight should be avoided.

# **HEALTH AND SAFETY**

Please see separate safety data sheet.

www.scottbader.com



Scott Bader d.o.o Croatia, 10000 Zagreb, Radnička cesta 173i

Tel: +385 1 2406-440 Email: info@scottbader.hr

© 2021 ScottBader Co Ltd, May 2021 | Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.