



# CRESTABOND<sup>®</sup>

Primerless MMA Structural Adhesives



 **ADHESIVES** by  
SCOTT BADER

# CRESTABOND®

Primerless MMA Structural Adhesives

Scott Bader is a global company with over 40 years experience in designing and manufacturing high quality adhesives.

Scott Bader benefits from an industry leading technical support team available to assist customers with technical advice.

Scott Bader also boasts in house laboratory testing facilities allowing for a rapid response to customer requests.

The Crestabond® range of M7 / PP (1:1) and M1 (10:1) structural adhesives are unique to the market due to the incorporation of our novel tougheners.

The Crestabond® range of adhesives benefits from a range of working times to suit different applications.




# Market Applications



## Marine

from kayaks to super yachts



## Land & transportation

buses, coaches, cars, trains and trucks



## Building & construction

doors, windows and cladding



## Wind energy

blades, housing and nacelles



## Recreational vehicles

motorhomes and caravans



## Agricultural vehicles

tractors, diggers, off-road and combine harvesters

## Guide To Bonding

### Check first

- ▶ Product is within shelf life
- ▶ Cartridge has been stored correctly
- ▶ No obvious defect or damage to cartridge
- ▶ No blockages at the cartridge outlet
- ▶ Correct static mixing nozzle is being used

### Key points

- ▶ Higher or lower working temperatures will cause the working time to decrease or increase
- ▶ Static mixers must always be discarded after use
- ▶ Operating temperature of Crestabond® is from -40°C up to 100°C

### 3 main groups of substrates to bond to:

#### Metals

- ▶ Some surface cleaning is required – remove any obvious dirt, grease, oxidation and other contaminants with either acetone, MEK or IPA
- ▶ Galvanised or zinc coated metals should be bonded using the Crestabond® M7 (1:1) range
- ▶ When bonding cold rolled steel (CRS), ensure that the substrate has been cleaned, abraded and then cleaned once more in order to achieve the best results

#### Composites

- ▶ Some surface cleaning is required – remove any obvious dirt, grease, oxidation and other contaminants with either acetone, MEK or IPA
- ▶ Gelcoat substrates need to be cleaned and may require a light abrasion with a 100-140 grit sandpaper and a further clean
- ▶ All composites can be bonded with Crestabond®

#### Plastics

- ▶ Some surface cleaning is required – remove any obvious dirt, grease, oxidation and other contaminants with either acetone, MEK or IPA
- ▶ For bonding low surface energy plastics such as Polypropylene (PP), Polyethylene (PE) and other Polyolefins, Crestabond® PP-04 must be used

# Crestabond® Features & Customer Benefits

## Crestabond® features

Primerless adhesives



Dramatically enhances production efficiency and reduces consumable costs

Minimal surface preparation



Reduces dust emissions and preparation time

Excellent fatigue and impact resistance



Confidence in the longevity of the finished product

Range of working and fixture times



Optimises production cycles to reduce manufacturing costs

Good gap filling capability



Adhesive can be used in multiple applications

Bonds dissimilar substrates



Provides flexibility in structure designs

## Crestabond® Dispensing Equipment

- ▶ The Crestabond® cartridges can be used with a manual or pneumatic gun. Suitable dispense guns and static mixers are available from Scott Bader
- ▶ Crestabond® adhesives can be dispensed directly from pails and drums using an automated 1:1 or 10:1 dispensing machine
- ▶ Scott Bader technical support can provide advice on appropriate dispensing equipment





# Adhesive Selection Guide

Selection of the appropriate product is essential for long-term adhesion and durability.

Crestabond® Product	Description	Colour	Mix ratio by volume	Viscosity (cP)	Working Time (mins)	*Fixture Time (mins)	Tensile Strength (MPa)	Tensile Modulus (MPa)	Elongation at break (%)	Gap Fill (mm)
M1-02	Universal Bonder	Black	10:1	100,000 - 140,000	1 - 2	2 - 3	12 - 16	600 - 1000	80 - 100	1 - 15
M1-04	Universal Bonder	Black	10:1	100,000 - 140,000	3 - 5	8 - 10	16 - 20	600 - 1000	80 - 100	1 - 15
M1-05	Universal Bonder	Black	10:1	100,000 - 140,000	4 - 7	12 - 18	16 - 20	600 - 1000	80 - 100	1 - 15
M1-10	Universal Bonder	Black	10:1	100,000 - 140,000	8 - 12	16 - 23	16 - 20	600 - 1000	80 - 100	1 - 15
M1-20	Universal Bonder	Black	10:1	100,000 - 140,000	16 - 22	25 - 35	16 - 20	600 - 1000	80 - 100	1 - 25
M1-30	Universal Bonder	Black	10:1	200,000 - 240,000	25 - 35	60 - 80	18 - 22	600 - 1000	100 - 130	1 - 50
M1-60HV	Universal Bonder	Green	10:1	340,000 - 380,000	50 - 70	150 - 180	22 - 26	1200 - 1600	50 - 70	1 - 50
M1-90HV	Universal Bonder	Green	10:1	340,000 - 380,000	80 - 100	210 - 240	22 - 26	1200 - 1600	50 - 70	1 - 50
M7-05	Universal Bonder	Off White or Black	1:1	30,000 - 70,000	4 - 7	18 - 22	22 - 25	1200 - 1700	25 - 30	1 - 5
M7-15	Universal Bonder	Off White or Black	1:1	30,000 - 70,000	10 - 20	30 - 45	22 - 25	1200 - 1700	25 - 30	1 - 5
PP-04	Low surface energy Bonder	Off White	1:1	70,000 - 140,000	3 - 5	165 - 180	12 - 17	800 - 1200	2 - 5	0.5 - 5

Based on laboratory results

\*Time taken at 23oC to achieve 1.4MPa strength in lap-shire tests according to BS ISO 4587

## Pack sizes

### Cartridges

#### M1 (10:1) range

- ▶ 50ml side-by-side
- ▶ 400ml coaxial
- ▶ 825ml side-by-side

#### M7 and PP (1:1) Range

- ▶ 50ml side-by-side
- ▶ 400ml side-by-side

### Bulk

- ▶ 20 Litre/ 18kg pails
- ▶ 200 Litre/ 180kg drums

► **Step 1** Choose the adhesive with optimal working and fixture times

### How to order bulk packed materials

Product	Adhesive	Activator
M1-02	M1-02 Adhesive	Activator 4
M1-04	M1-04/05 Adhesive	Activator 4
M1-05	M1-04/05 Adhesive	Activator 1 Black
M1-10	M1-10 Adhesive	Activator 1 Black
M1-20	M1-20 Adhesive	Activator 1 Black
M1-30	M1-30 Adhesive	Activator 1 Black
M1-60HV	M1-60HV Adhesive	Activator 2 Green
M1-90HV	M1-90HV Adhesive	Activator 2 Green
M7-05	M7-05 Adhesive or M7-05 Adhesive Black	M7-05 Activator
M7-15	M7-15 Adhesive or M7-15 Adhesive Black	M7-15 Activator

Product	GRP	Stainless Steel	Aluminium	Powder Coated Steel	Cold Rolled Steel	Galvanised	ABS	Acrylic	Polycarbonate	PVC	PP/PE & TPO
M1-02	✓	✓	✓	✓	✓		✓	✓	✓	✓	
M1-04	✓	✓	✓	✓	✓		✓	✓	✓	✓	
M1-05	✓	✓	✓	✓	✓		✓	✓	✓	✓	
M1-10	✓	✓	✓	✓	✓		✓	✓	✓	✓	
M1-20	✓	✓	✓	✓	✓		✓	✓	✓	✓	
M1-30	✓	✓	✓	✓	✓		✓	✓	✓	✓	
M1-60HV	✓	✓	✓				✓	✓	✓	✓	
M1-90HV	✓	✓	✓				✓	✓	✓	✓	
M7-05	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	
M7-15	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓	
PP-04	✓	✓	✓		✓		✓	✓	✓	✓	✓

► **Step 2** Check the adhesive bonds the required substrates:

- Composites
- Metals
- Plastics
- Galvanised

► **Step 3** Arrange a demonstration or trial by contacting your local Scott Bader representative or email [enquiries@scottbader.com](mailto:enquiries@scottbader.com)





Making a **positive** difference

## Scott Bader Commonwealth Ltd - A common trusteeship company

### Scott Bader Group Companies

#### Head Office

##### Scott Bader Company Limited

Wollaston, England

**Tel:** +44 (0)1933 663100

**Fax:** +44 (0)1933 666139

**Email:** enquiries@scottbader.com

#### Scott Bader France

Amiens, France

**Tel:** +33 3 22 66 27 89

**Fax:** +33 3 22 66 27 80

**Email:** info\_distribution@scottbader.fr

#### Scott Bader Spain

Barcelona, Spain

**Tel:** +34 93 553 1162

**Fax:** +34 93 553 1163

**Email:** diazs@scottbader.es

#### Scott Bader Germany

Weiden, Germany

**Tel:** +49 961 401 84474

**Fax:** +49 961 401 84476

**Email:** composites@scottbader.de

#### Scott Bader Ireland

Dublin, Ireland

**Tel:** +353 1801 5656

**Fax:** +353 1801 5657

**Email:** composites@scottbader.ie

#### Scott Bader Scandinavia AB

Falkenberg, Sweden

**Tel:** +46 346 10100

**Fax:** +46 346 59226

**Email:** composites@scottbader.se

#### SB Eastern Europe s.r.o

Mimon II, Czech Republic

**Tel:** +420 (0) 487 863 880

**Fax:** +420 (0) 485 111 254

**Email:** miro@sbee.cz

#### Scott Bader Croatia

Zagreb, Croatia

**Tel:** +385 1 240 6440

**Fax:** +385 1 240 4573

**Email:** info@scottbader.hr

#### Scott Bader North America

Stow, OH,

USA

**Tel:** +1 330 920 4410

**Fax:** +1 330 920 4415

**Email:** info@scottbader-na.com

#### Scott Bader South Africa

Hammarsdale, South Africa

**Tel:** +27 31 736 8500

**Fax:** +27 31 736 8511

**Email:** composites@scottbader.co.za

#### Scott Bader Middle East Limited

Dubai, United Arab Emirates

**Tel:** +971 481 50 222

**Fax:** +971 488 35319

**Email:** info@scottbader.ae

#### Scott Bader Asia Pacific

Shanghai, China

**Tel:** +86 (21) 5298 7778

**Fax:** +86 (21) 5298 8889

**Email:** info@scottbader.cn

#### Satyen Scott Bader Pvt. Ltd

Mumbai, India

**Tel:** + 91 22 4220 1555

**Fax:** + 91 22 2491 1262

**Email:** info@satyenpolymers.com

#### NovaScott Especialidades Químicas Ltda

Civit II, Serra,

ES 29165-973,

Brazil

**Tel:** +55 27 3298-1100

**Email:** info@novascott.com.br

#### Scott Bader Japan KK

Room #708, NISSO #18 bldg., 3-7-18,

Shin Yokohama, Kohoku-ku, Yokohama,

Kanagawa pref., 222-0033, Japan

**Tel:** +81 (0)90-5530-4427

**Email:** yoshio\_mizuno@scottbader.com



+44 (0)1933 663100

enquiries@scottbader.com

**scottbader.com**



# ADHESIVES

Crestabond® | Crestomer® | Crestafix®