

# CRESTAKYD<sup>®</sup> 10-4007

## Long oil alkyd

### INTRODUCTION

CRESTAKYD 10-4007 is an air drying alkyd that has excellent brushability & flow characteristics, as well as good gloss retention & weathering resistance.

### CHARACTERISTICS (Not to be taken as a specification)

Solids content	%	70
Oil type		linoleic
Oil content	%	62
Solvent		High flash aliphatic naphtha, D80
Acid value (base resin)	mgKOHg-1	13 max
Viscosity @ 25°C, sp 4/10rpm	mPa·s	7500
Colour	Gardner	6 max
Relative density at 20°C	g/cm <sup>3</sup>	0.96

## APPLICATIONS

CRESTAKYD 10-4007 has been specifically formulated for use in artist's paints and for applications requiring higher flash points.

### Drier Recommendation:

0.2% zirconium, 0.05% cobalt and 0.1% calcium, calculated as metals on resin solids or suitable combination driers.

## PACKAGING

CRESTAKYD 10-4007 can be supplied in drums. Bulk deliveries are by road tanker.

## STORAGE

CRESTAKYD 10-4007 The resin should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 0°C and 30°C. Exposure to direct sunlight should be avoided.

## HEALTH & SAFETY

Please see separate material safety data sheet.

Issue No. 8 Feb-17

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

 **SCOTT BADER d.o.o.**

CROATIA , 10000 ZAGREB, Radnička cesta 173i.

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: [info@scottbader.hr](mailto:info@scottbader.hr)

