



Product overview

TEXICRYL[®] 13-216 is an APEO free self-cross linking acrylic copolymer emulsion binder with superior adhesion and binding properties, designed for use in textile printing. Suitable for use with all printing machines e.g. roller machines, flat bed screens, rotary screens ect.

Characteristics (Not to be taken as a specification)	
Solids content	45%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	100 mPa s
pH	5
Particle Size nm	240
Minimum film formation temperature*	2°C
Glass transition temperature	-14°C

*Determined by metal bar with temperature gradient

Application

TEXICRYL[®] 13-216 can be used to formulate textile prints with the following properties.

- Very soft handle
- Excellent rub resistance and fastness
- Excellent runnability
- Low thickener demand
- Excellent electrolyte bleed/ flush resistance
- Excellent compatibility with all non-ionic and anionic textile auxiliaries
- Possible to print without screen blockages even with 73 micron screens

TEXICRYL[®] 13-216 is suitable for printing on cotton, polyester and blended fabrics using pigments. It can be added either directly or to the print paste or it can be used to prepare a pre-thickened vehicle (ie: water, binder and thickener)

TEXICRYL[®] 13-216 is an excellent binder for back coatings and foam coatings. This product is also recommended as an adhesive for non-woven fabrics and as an adhesive for electrostatically applied flock.

TEXICRYL[®] 13-216 is compatible with harder acrylic or styrene acrylic polymers designed for this market, to give films of immediate hardness and can be subsequently thickened with acrylic emulsion thickeners.

Packaging and storage

TEXICRYL[®] 13-216 maybe supplied in drums or IBC's (please check with your local representative).

Bulk deliveries are by road tanker.



TEXICRYL[®] 13-216 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost and extended periods of direct sunlight should be avoided.

Health and safety

Please see separate material safety data sheet

© 2021 Scott Bader Company Limited, March 2020, Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.