



## Technical Data Sheet

### PRODUCT OVERVIEW

TEXICRYL® 13-013 is a styrene acrylic copolymer emulsion containing a plasticizer.

TEXICRYL 13-013 is suitable for paints, sealants and soft fillers applications.

#### CHARACTERISTICS

(Not to be taken as a specification)

Solids content	55%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	800 mPa s
pH	8.25
Minimum film formation temperature*	< 0 °C

\*Determined by metal bar with temperature gradient

### APPLICATION

TEXICRYL 13-013 has been developed for sealants, acrylics and highly filled putties.

TEXICRYL 13-013 gives excellent adhesion on substrates and even at low temperature, the flexibility is good.

### PACKAGING AND STORAGE

TEXICRYL 13-013 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-013 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

### HEALTH AND SAFETY

Please see separate material safety data sheet.

[www.scottbader.com](http://www.scottbader.com)



#### Scott Bader UK Office

Wollaston  
Wellingborough  
Northants  
NN29 7RL  
UK

Tel: +44 (0)1933 666738

email: [enquiries@scottbader.com](mailto:enquiries@scottbader.com)