

Texicryl[®] 13-078

Acrylic Dispersions

Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-078 is a styrene acrylic copolymer emulsion, designed primarily as a binder for high performance ceramic tile adhesives.

CHARACTERISTICS (Not to be taken as a specification)	
Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	100 mPa s
рH	8.3
Particle size	250 nm
Minimum film formation temperature*	18 ℃
Glass transition temperature	20 °C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-078 has been designed to be formulated with a wide range of filler types into water resistant tile adhesives and grouts.

PACKAGING AND STORAGE

TEXICRYL 13-078 is be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-078 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com



Scott Bader UK Office Wollaston Wellingborough Northants NN29 7RL UK

Tel: +44 (0)1933 666738 email: enquiries@scottbader.com

© 2020 ScottBader Co Ltd, August 2020 | Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.