



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-219 is a self-crosslinking styrene acrylic copolymer emulsion for use as a binder in the manufacture of spray-bonded synthetic fibre waddings. This product is also ideal as a stiffener for window blinds.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	46%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	200 mPa s
pH	7.0
Particle size	150 nm
Minimum film formation temperature*	15°C
Glass transition temperature	30°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-219 has been developed for use in surface bonding and through-bonding of synthetic fibre wadding. It will effectively prevent penetration of the fibres through the cover fabric, preserve the high loft of the wadding and facilitate handling during the making-up process. It has excellent heat and light-stability, as well as good wash and dry-clean solvent resistance.

Drying and Curing

Cure of emulsion binders is dependent on the polymer type, catalyst concentration, temperature and time.

TEXICRYL 13-219 is supplied ready-catalysed and, after drying, must be cured for 2-3 minutes at 140°C. It is recommended that synthetic fibre waddings processed with TEXICRYL 13-219 be dried and cured in hot-air ovens with efficient air movement to ensure removal of water vapour during the drying phase.

When dried and cured under these conditions, TEXICRYL 13-219 will confer dry-clean resistance, wash-fastness and good recovery from compression. TEXICRYL 13-219 has an indefinite pot life at normal spraybonding concentrations (10-25% solids content).

TEXICRYL 13-219 has a non-detectable formaldehyde level according to Oeko-Tex® testing, ISO 14184-1 2011.

PACKAGING AND STORAGE

TEXICRYL 13-219 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-219 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Protect from freezing and direct sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com



© 2020 ScottBader Co Ltd, September 2020 | Issue No. 1

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com