



## Technical Data Sheet

### PRODUCT OVERVIEW

TEXICRYL® 13-223 is self crosslinking styrene acrylic copolymer emulsion with high solvent and dry clean resistance.

#### CHARACTERISTICS

(Not to be taken as a specification)

Solids content	45%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	100 mPa s
pH	6.0
Particle size	210 nm
Minimum film formation temperature*	<2 °C
Glass transition temperature	11°C

\*Determined by metal bar with temperature gradient

### APPLICATION

TEXICRYL 13-223 is used in textile and non woven applications where a medium soft handle is required.

### PACKAGING AND STORAGE

TEXICRYL 13-223 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-223 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

### HEALTH AND SAFETY

Please see separate material safety data sheet.

[www.scottbader.com](http://www.scottbader.com)

#### Scott Bader UK Office

Wollaston  
Wellingborough  
Northants  
NN29 7RL  
UK

Tel: +44 (0)1933 666738

email: [enquiries@scottbader.com](mailto:enquiries@scottbader.com)