



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-224 is self crosslinking styrene acrylic copolymer emulsion with soft handle and good wet scrub resistance properties.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	41%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	300 mPa s
pH	5.5
Particle size	210 nm
Minimum film formation temperature*	<2 °C
Glass transition temperature	-9°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-224 gives excellent binding properties for pigment printing of textiles. It maybe used on both rotary and flat frameworks.

TEXICRYL 13-224 has a non-detectable formaldehyde level according to Oeko-Tex® testing, ISO 14184-1 2011.

PACKAGING AND STORAGE

TEXICRYL 13-224 is be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-224 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Protect from freezing and direct sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com