



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-294 is a low formaldehyde, self-crosslinking, acrylic copolymer emulsion designed for use in a range of non-woven and textile applications.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	48%
Viscosity at 25°C (RV8 #3 20 rpm)	650 mPa s
pH	4.5
Particle size	285 nm
Glass transition temperature	-35 °C

APPLICATION

TEXICRYL 13-294 has been designed for non-woven and textile applications where a firm hand, good solvent resistance, excellent adhesion to natural and synthetic fibres and low formaldehyde emissions are important.

PACKAGING AND STORAGE

TEXICRYL 13-294 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-294 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com