



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-314 is an acrylic copolymer emulsion that can be hydrolysed under alkaline conditions for use as a thickener in aqueous-based systems.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	40%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	30 mPa s
pH	3.0
Specific gravity at 25°C	1.09 g/cm ³
Particle size	220 nm
Glass Transition Temperature	25°C

APPLICATION

TEXICRYL 13-314 has been specifically designed for use in aqueous-based formulations.

PACKAGING AND STORAGE

TEXICRYL 13-314 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-314 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Protect from frost and extended exposure to sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com