



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-318 is a hydrophobically modified alkali swellable emulsion designed for use as a rheology modifier in water-based formulations. It is highly effective in modifying viscosities at low shear rates to avoid both settling and sagging.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	30%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	25 mPa s
pH	3.0
Specific gravity at 25°C	1.05
Particle size	110 nm

APPLICATION

TEXICRYL 13-318 has been designed for use in the formulation of textured coatings, woodstains, paints and waterborne coating systems.

PACKAGING AND STORAGE

TEXICRYL 13-318 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-318 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Protect from frost and extended exposure to direct sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com