



PRODUCT OVERVIEW

TEXICRYL® 13-526 is a high performance styrene acrylic copolymer emulsion designed for use in cold seal adhesive applications.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 20 rpm)	200 mPa s
pH	4.5
Minimum film formation temperature*	12°C
Glass transition temperature	19°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-526 is designed for use in cold seal adhesive formulations.

PACKAGING AND STORAGE

TEXICRYL 13-526 is supplied in 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-526 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com