



### PRODUCT OVERVIEW

TEXICRYL® 13-528 is a high performance styrene acrylic copolymer emulsion designed for use in cold seal adhesive applications.

#### CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 20 rpm)	100 mPa s
pH	6.5
Minimum film formation temperature*	10°C
Glass transition temperature	9°C

\*Determined by metal bar with temperature gradient

### APPLICATION

TEXICRYL 13-528 is designed for use in cold seal adhesive formulations.

### PACKAGING AND STORAGE

TEXICRYL 13-528 is supplied in 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-528 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

### HEALTH AND SAFETY

Please see separate material safety data sheet.

[www.scottbader.com](http://www.scottbader.com)

#### Scott Bader UK Office

Wollaston  
Wellingborough  
Northants  
NN29 7RL  
UK

Tel: +44 (0)1933 666738

email: [enquiries@scottbader.com](mailto:enquiries@scottbader.com)