



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-601 is a pure acrylic copolymer emulsion designed for use in both interior and exterior coating applications.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 100 rpm)	75 mPa s
pH	8.5
Particle size	140 nm
Minimum film formation temperature*	0°C
Glass transition temperature	8°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-601 is designed for use in the formulation of solvent free decorative coatings with excellent durability and low dirt pick up. Other applications include artist's colours and hobby paints.

PACKAGING AND STORAGE

TEXICRYL 13-601 is supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-601 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Protect from frost and extended exposure to direct sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com