



## Technical Data Sheet

### PRODUCT OVERVIEW

TEXICRYL® 13-602 is a styrene acrylic copolymer emulsion designed for use in flexible fillers and caulks.

#### CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 4, 100 rpm)	1500 mPa s
pH	8
Minimum film formation temperature*	25 °C
Glass transition temperature	30 °C

\*Determined by metal bar with temperature gradient

### APPLICATION

TEXICRYL 13-602 is designed for flexible fillers, caulks and sealant applications.

### PACKAGING AND STORAGE

TEXICRYL 13-602 may be supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-602 should be stored in the original, unopened and undamaged containers in a dry place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

### HEALTH AND SAFETY

Please see separate material safety data sheet.

[www.scottbader.com](http://www.scottbader.com)

#### Scott Bader UK Office

Wollaston  
Wellingborough  
Northants  
NN29 7RL  
UK

Tel: +44 (0)1933 666738

email: [enquiries@scottbader.com](mailto:enquiries@scottbader.com)