



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-607 is a pure acrylic copolymer emulsion designed for use in a broad range of formulations requiring low VOC, low water uptake and excellent water whitening resistance.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (100 rpm)	450 mPa s
pH	8.5
Particle size	150 nm
Minimum film formation temperature	2°C
Tg	12°C

APPLICATION

TEXICRYL 13-607 is designed for use in artist's colour formulations as well as for low VOC interior and exterior coating systems. It also shows good water blanching resistance.

PACKAGING AND STORAGE

TEXICRYL 13-607 is supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-607 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Protect from frost and extended exposure to direct sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com