



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-616 is a self crosslinking acrylic copolymer emulsion designed for use in high performance coatings.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	48%
Viscosity at 25°C (Brookfield RVT, Spindle 2, 20 rpm)	250 mPa s
pH	8.5
Particle size	120 nm
Minimum film formation temperature	18°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-616 is designed for use in high performance coatings with superior water, chemical and blocking resistance.

PACKAGING AND STORAGE

TEXICRYL 13-616 is supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-616 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com



Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com