



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-619 is a styrene acrylic copolymer emulsion designed for formulation of co-solvent free construction adhesives.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (Brookfield RVT, Spindle 1, 20 rpm)	350 mPa s
pH	8.3
Particle size	200 nm
Minimum film formation temperature	10°C
Glass transition temperature	15°C

APPLICATION

TEXICRYL 13-619 can be used in the formulation of high performance water resistant tile adhesives, fix and grouts and general purpose fillers.

PACKAGING AND STORAGE

TEXICRYL 13-619 is supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-619 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com