



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-620 is an APEO free pure acrylic copolymer emulsion designed for use in the building and construction industry. The polymer offers improved adhesion to various substrates and superior elasticity to relevant mixtures.

CHARACTERISTICS

(Not to be taken as a specification)

| | |
|--|------------|
| Solids content | 60% |
| Viscosity at 25°C (Brookfield RVT, Spindle 4, 20 rpm) | 2250 mPa s |
| pH | 8.0 |
| Minimum film formation temperature | <0°C |
| Glass transition Temperature | -55°C |

APPLICATION

TEXICRYL 13-620 is used in the formulation of flexible mineral sealings, crack-bridging systems, waterproof coatings, fillers, putties, polymer-modified cement and mortar based mixtures of all kinds.

PACKAGING AND STORAGE

TEXICRYL 13-620 is supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-620 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com