



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-665 is designed for use in a broad range of formulations where low VOC is required.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	50%
Viscosity at 25°C (100 rpm)	200 mPa s
pH	8.5
Particle size	140 nm
Minimum film formation temperature	8°C
Tg	18°C

APPLICATION

TEXICRYL 13-665 has been designed MIT free to meet the new regulatory requirements for artist's colour paints.

PACKAGING AND STORAGE

TEXICRYL 13-665 is supplied in drums and 1 tonne IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-665 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Protect from freezing and direct sunlight.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com