



## Technical Data Sheet

### PRODUCT OVERVIEW

TEXICRYL® 13-682 is the APEO free Styrene Acrylic copolymer emulsion designed for use in high performance roof coating compounds and in a wide range of water-based paints.

#### CHARACTERISTICS

(Not to be taken as a specification)

Solids content	47% ± 1
Viscosity at 25°C (UK Viscometer RV8 Spindle 4 rpm 100)	1000 - 1500 cP
pH	7.5 - 8.5
Specific gravity at 25°C	1.02
Minimum film formation temperature*	± 8°C

### APPLICATION

TEXICRYL 13-682 is specifically recommended for the formulation of roof mastics and waterproofing compounds. It has exceptional water resistance after drying yet good water vapour transmission. Compounds made with TEXICRYL 13-682 stand up to prolonged ponded water conditions.

TEXICRYL 13-682 forms an extremely tough, very flexible film, with excellent adhesion to common building materials. Due to its tough film and high water resistance, dirt pick-up with TEXICRYL 13-682 is minimal.

### PACKAGING AND STORAGE

TEXICRYL 13-682 is supplied in 200 kg lacquer-lined metal drums and minibulk containers. Bulk supplies are delivered by road tanker.

TEXICRYL 13-682 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Protect from direct sunlight.

### HEALTH AND SAFETY

Please see separate material safety data sheet.

[www.scottbader.com](http://www.scottbader.com)

**Scott Bader UK Office**

Wollaston  
Wellingborough  
Northants  
NN29 7RL  
UK

**Tel:** +44 (0)1933 666738

**email:** [enquiries@scottbader.com](mailto:enquiries@scottbader.com)