



Technical Data Sheet

PRODUCT OVERVIEW

TEXICRYL® 13-824 is a styrene- acrylic copolymer emulsion that can be coalesced to form a solvent and plasticiser resistant film.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	45%
Viscosity (Brookfield RVT, Spindle 2, 100 rpm)	190 mPa s
pH	8.5
Particle size	80 nm
Minimum film formation temperature *	70°C
Glass transition temperature	66°C

*Determined by metal bar with temperature gradient

APPLICATION

TEXICRYL 13-824 has been developed for the formulation of plasticiser resistant inks.

PACKAGING AND STORAGE

TEXICRYL 13-824 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-824 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com

Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com