



PRODUCT OVERVIEW

TEXICRYL® 13-828 is a highly efficient alkali swellable emulsion designed for water-based printing ink formulations.

CHARACTERISTICS

(Not to be taken as a specification)

Solids content	44%
Viscosity (Brookfield RVT, Spindle 2, 100 rpm)	80 mPa s
pH	5.0
Particle size	165 nm
Glass transition temperature	145°C
Acid Value	176 mg KOH/g

APPLICATION

TEXICRYL 13-828 has been designed for use in flexographic inks for corrugated board. It is also suitable as a pigment grinding medium and let down vehicle.

PACKAGING AND STORAGE

TEXICRYL 13-828 is supplied in drums or IBC's (please check with your local representative). Bulk deliveries are by road tanker.

TEXICRYL 13-828 should be stored in the original, unopened and undamaged containers in a dry, well ventilated place at temperatures between 5°C and 30°C. Exposure to frost should be avoided.

HEALTH AND SAFETY

Please see separate material safety data sheet.

www.scottbader.com



Scott Bader UK Office

Wollaston
Wellingborough
Northants
NN29 7RL
UK

Tel: +44 (0)1933 666738

email: enquiries@scottbader.com