



Introduction

espol™ 41.00 is a non-accelerated isophthalic neopentyl glycol (ISO-NPG) polyester resin suitable for aggressive marine applications. The resin has been approved by IRS (Indian Registrar of shipping) for usage on ships and other marine transport vehicles. It has been specifically formulated for resistance to sea water, offering superior osmotic stability alongside excellent mechanical properties.

Applications

espol™ 41.00 is designed for laminates for hand lamination & casting process primarily. It can be used with all types of glass fibre such as chopped strand mat, woven roving and multi axials. It brings in excellent mechanical strength & rigidity along with long term durability. It is designed for rapid tack free cure.

Formulation

espol™ 41.00 should be allowed to attain workshop temperature (25°C - 30°C) before use. Stir well by hand, or with a low shear mixer to avoid aeration, and then allow to stand to regain thixotropy. espol™ 41.00 requires the addition of cobalt promoter and catalyst to start the curing reaction.

The recommended accelerator is Cobalt (1% solution in styrene) which should be added to the resin at 1 - 2% and thoroughly incorporated into the resin, using a low shear mechanical stirrer where possible.

The recommended catalyst is MEKP (50%) which should be added to the resin at 1 - 2% and thoroughly incorporated into the resin, using a low shear mechanical stirrer where possible.

(Please consult our Technical Support Department if other catalysts are to be used).

N.B. Catalyst and accelerator must not be mixed directly together since they can react with explosive violence.

Physical data - uncured

The following tables give typical properties of espol™ 41.00 when tested to IS 6746-1994 (Reaffirmed 2005).

Property	Unit	Value
Appearance	-	Light pale-yellow liquid
Specific gravity	-	1.09 – 1.13
Viscosity at 25°C*	cP	480 - 720
Acid Value	mg-KOH/gm	13 - 16
Volatile Content	%	33 - 40
Geltime at 25°C**	Minutes	14 - 20
Peak Exotherm Temp**	°C	145 - 165
Stability from date of manufacture when stored in accordance with storage recommendations.	months	3

*Viscosity measured using Brookfield (RVT Model) Viscosity SPL 2 / SPD 10

**100g resin + 2ml Cobalt (1%) + 1.5ml MEKP (50%) Catalyst.

Physical data - cured

Property	Unit	Fully cured*
Barcol hardness		40
Deflection temperature under load* (1.80MPa)	°C	75
Tensile strength*	MPa	50 -65
Tensile modulus*	MPa	3000 - 3400
Elongation at break*	%	2.0 - 2.5
Flexural strength*	MPa	100 - 120
Flexural modulus*	MPa	3200 - 3600

*Curing Schedule - 24 hours at 20°C, 6 hours at 80°C.

Post Curing

Satisfactory laminates for many applications can be made from espol™ 41.00 by curing at workshop temperature (25°C). For optimum properties, however, laminates should be post-cured before being put into service. The laminate should be allowed to cure for 24 hours at 25°C, and then be oven cured for a minimum of 6 hours 80°C.

Storage

espol™ 41.00 should be stored between 5°C and 25°C in the original, unopened container in a dry, well ventilated place. Protect from freezing and direct sunlight. Avoid contact with oxidising agents. If stored outside of these recommendations, shelf life will be significantly reduced.

Packaging

espol™ 41.00 is available in 35kg, 220kg and bulk containers.

Health and Safety

Please see separate Material Safety Data Sheet.

© 2022 Scott Bader Company Limited, November 2022, Issue No. 1, GTC ES4100

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.